



TEST REPORT TUCHENG

Date of Issue: Mar.23,2023 Date of Receipt and Test Start: Mar.15,2023

Report No.: TAF2C182 Quantity: 1PC Page Order/Pages: (P1/2) Ref. No.: NIL


Report Title: Shiuian Jia Industrial Co., Ltd.(T5282) Item: Knitted Fabric

Address: 7f, No. 651-3, Chung Cheng Rd., Hsin-chuang District, New Taipei City, Taiwan,(R.O.C.)

Test Items	Test Results	Test Methods
Transmission(%)	Mean UVB	0.3
	Mean UVA	3.7
Blocking(%)	Mean UVB	99.7
	Mean UVA	96.3
Ultraviolet Protection Factor (UPF)	153	

This test report is for reference only and should not be used as a formal document.  
Instrument: SOLAR LIGHT SPF-290AS

Note: Sample description is given by the client: S12660-A1 100% POLYESTER DRY REVERSE PK WITH WICKING 130G/SM 58" CUTTABLE



- Note: 1.This report is only responsible for the submitted sample(s), which will be kept for one month period.
- 2.This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- 3.The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Jui-hung kao  
Taiwan Textile Research Institute  
Director, Department of Testing and Certification

Department of Testing and Certification, Taiwan Textile Research Institute  
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)  
Tel : +886-2-22670321 ext. 7107, 7110  
Fax : +886-2-22675108 , +886-2-22689839



**TEST REPORT TUCHENG**

Date of Issue: Mar.23,2023 Date of Receipt and Test Start: Mar.15,2023

Report No.: TAF2C182 Quantity: IPC Page Order/Pages: (P2/2) Ref. No.: NIL


Report Title: Shiuan Jia Industrial Co., Ltd.(T5282) Item: Knitted Fabric

Address: 7f, No. 651-3, Chung Cheng Rd., Hsin-chuang District, New Taipei City, Taiwan,(R.O.C.)

Test Items	Test Results	Test Methods
Wetting Time (s)	Top surface	3
	Bottom surface	3
Absorption rate (%/s)	Top surface	24
	Bottom surface	36
Maximum wetted radius (mm)	Top surface	23
	Bottom surface	26
Spreading speed (mm/s)	Top surface	5.3
	Bottom surface	6.0
Accumulative One-Way Transport Index(%)		265
OMMC		0.67
Drying Characteristic	Drying Time(min)	9.6

This test report is for reference only and should not be used as a formal document.

Note: Sample description is given by the client: S12660-A1 100% POLYESTER DRY REVERSE PK WITH WICKING  
130G/SM 58" CUTTABLE



- Note: 1.This report is only responsible for the submitted sample(s), which will be kept for one month period.  
2.This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.  
3.The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Jui-hung kao  
Taiwan Textile Research Institute  
Director,  
Department of Testing and Certification

Department of Testing and Certification, Taiwan Textile Research Institute  
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R. O. C.)  
Tel : +886-2-22670321 ext. 7107, 7110  
Fax : +886-2-22675108 , +886-2-22689839